

ISOFLEX TOPAS L 30

Low-temperature grease



Benefits for your application

- Synthetic low-temperature grease
- Good corrosion protection
- Resistant to ageing and oxidation
- Suitable for high speeds

Description

ISOFLEX TOPAS L 30 is a high-speed and low-temperature grease for rolling and plain bearings. It is based on a synthetic hydrocarbon oil and lithium soap. This special grease is resistant to oxidation and ageing, protects against corrosion and is water resistant.

Application

For rolling and plain bearings requiring a low starting and running torque, such as in automotive engineering, machine tools and precision engineering. ISOFLEX TOPAS L 30 can also be used for slideways, bowden cables, door locks and small gears. Lubrication of tooth flanks of plastic/plastic gears and plastic/steel materials.

Application notes

The product is applied by brush, spatula or grease gun. Due to the great variety of different elastomers and plastics, their compatibility with the grease has to be checked prior to series application.

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes	ISOFLEX TOPAS L 30
Tube 45 g	+
Can 1 kg	+
Bucket 25 kg	+

Product data	ISOFLEX TOPAS L 30
Article number	004142
Lower service temperature	-60 °C / -76 °F
Upper service temperature	120 °C / 248 °F
Colour space	beige
Texture	homogeneous
Texture	short-fibred
Density at 20 °C	approx. 0.86 g/cm ³
Worked penetration, DIN ISO 2137, 25 °C, lower limit value	355 x 0.1 mm
Worked penetration, DIN ISO 2137, 25 °C, upper limit value	385 x 0.1 mm
Kinematic viscosity of the base oil, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 40 °C	approx. 17 mm ² /s
Kinematic viscosity of the base oil, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 100 °C	approx. 4 mm ² /s
Shear viscosity at 25 °C, shear rate 300 s ⁻¹ , equipment: rotational viscometer, lower limit value	500 mPas



ISOFLEX TOPAS L 30

Low-temperature grease

Product data	ISOFLEX TOPAS L 30
Shear viscosity at 25°C, shear rate 300 s ⁻¹ , equipment:rotational viscometer, upper limit value	2 000 mPas
Copper corrosion, DIN 51811, (lubricating grease), 24h/100°C	1 - 100 corrosion degree
Drop point, DIN ISO 2176, IP 396	>= 190 °C
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	36 months

Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 80 years.

**Klüber Lubrication München SE & Co. KG /
Geisenhausenerstraße 7 / 81379 München / Germany /
phone +49 89 7876-0 / fax +49 89 7876-333.**

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München SE & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München SE & Co. KG and if source is indicated and voucher copy is forwarded.