

Klübersynth VR 69-252 N

Special lubricating grease for drinking water taps containing e.g. EPDM and/or NBR elastomers



Benefits for your application

- Longer component life due to less friction and wear, especially in brass spindle valves.
- Prevention of stick-slip at high tightening torques and 500,000 load cycles.
- A lubricant for all components meeting all technical, design and chemical requirements, e.g. the German KTW and the French ACS Guidelines.
- Cost-saving as lubricant can be applied by brush or using fully automatic mass application techniques.

Description

Klübersynth VR 69-252 N is a tailor-made, highly adhesive, light-colored lubricating grease based on fatty oil, calcium soap and PTFE. With a carefully selected combination of active substances, this lubricant offers very good performance and high functionality combined with a long service life. Klübersynth VR 69-252 N clearly surpasses the load alternation requirement of 200,000 cycles at a closing force of 2.5 Nm and is therefore in full compliance with the European standard DIN EN 200. Klübersynth VR 69-252 N meets the new drinking water and plastics guideline (KTW) of the German Umweltbundesamt (Federal Environmental Agency) and conforms to the current French positive list for drinking water applications ACS.

These benefits help meet all your requirements.

Application

Klübersynth VR 69-252 N is used for the lubrication of all friction points in valves subject to mechanical loads and in some cases also for ceramic valves containing EPDM or NBR elastomers. Further applications are in locking and control

valves such as plug or ball valves, flaps, slides or other valves, and in shower and heating valves and fittings. Klübersynth VR 69-252 N may normally also be used for the lubrication of seals whenever an EPDM-compatible grease is required that is approved for drinking water applications.

Application notes

Klübersynth VR 69-252 N can be easily applied by means of brush, sponge, spatula, grease gun or other usual metering equipment.

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes	Klübersynth VR 69-252 N
Can 1 kg	+
Bucket 5 kg	+

Product data	Klübersynth VR 69-252 N
Article number	012273
NSF-H1 registration	152 147
Lower service temperature	-25 °C / -13 °F
Upper service temperature	100 °C / 212 °F
Density at 20 °C	approx. 0.97 g/cm ³
Colour space	beige
Worked penetration, DIN ISO 2137, 25 °C, lower limit value	280 x 0.1 mm
Worked penetration, DIN ISO 2137, 25 °C, upper limit value	310 x 0.1 mm



Klübersynth VR 69-252 N

Special lubricating grease for drinking water taps containing e.g. EPDM and/or NBR elastomers

Product data	Klübersynth VR 69-252 N
Shear viscosity at 25°C, shear rate 300 s ⁻¹ , equipment:rotational viscometer, upper limit value	8 000 mPas
Shear viscosity at 25 °C, shear rate 300 s ⁻¹ , equipment: rotational viscometer, lower limit value	4 000 mPas
Copper corrosion, DIN 51811, (lubricating grease), 24h/100°C	1 - 100 corrosion degree
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	12 months

Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 80 years.

**Klüber Lubrication München SE & Co. KG /
Geisenhausenerstraße 7 / 81379 München / Germany /
phone +49 89 7876-0 / fax +49 89 7876-333.**

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München SE & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München SE & Co. KG and if source is indicated and voucher copy is forwarded.