

Klübertemp HCB 83-402

High-temperature lubricant for roller chains in stenter frames



Your benefits at a glance

- Long relubrication intervals for high efficiency
- Resistant towards aggressive chemicals in textile softening and finishing agents
- Long-standing effective use at leading manufacturers of stenter frames

Your requirements – our solution

Due to increasing cost pressure, the textile industry is demanding chain lubricants offering ever higher thermal stability and longer relubrication intervals.

We developed Klübertemp HCB 83-402 to reduce your operating costs.

Klübertemp HCB 83-402 is a synthetic high-temperature lubricant for roller chains based on perfluorinated polyether oils and a new combination of PTFE solid lubricants. Klübertemp HCB 83-402 does not harden in continuous operation, extending machine availability.

Relubrication of friction points is also made easier. Selected base oils provide the optimum combination of evaporation stability and the right viscosity for operation. The lubricant remains in the friction point for longer and increases the life expectancy of your roller chain.

Klübertemp HCB 83-402 offers long relubrication intervals, reduced maintenance requirements and good wear protection to reduce your operating costs.

Application

Klübertemp HCB 83-402 was specially developed for the long-term lubrication of rolling bearings in roller chains of high-performance stenter frames. The lifetime of the anti-spreader chain determines the performance and efficiency of your entire plant. Drying, conditioning and heat-setting may involve temperatures above 200 °C. Additionally, chain and lubricant are in contact with aggressive media from softening and finishing agents.

Under these conditions, Klübertemp HCB 83-402 has proven to be a durable and reliable lubricant. Klübertemp HCB 83-402 is generally regarded as neutral towards elastomers and plastics (with the possible exception of perfluorinated rubber).

No negative effects are known when used with chain lubricants like Klüber PRIMIUM FLUID SPECIAL.

Application notes

Klübertemp HCB 83-402 can be applied using a spatula, brush or grease gun.

For optimum lubrication results, we recommend cleaning the friction points with white spirit 180/210 followed by Klüberalfa XZ 3-1 before using Klübertemp HCB 83-402 for the first time. The friction points must be clean and bright, i.e. free from oil, grease, perspiration and contamination. Then blow the surfaces with clean, dry compressed air or hot air to remove white spirit residues.

To optimise the service life of your equipment or if you have any other questions regarding your application, our experts will be pleased to help you. We look forward to hearing from you.

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes	Klübertemp HCB 83-402
Cartridge 800 g	+
Can 1 kg	+



Klübertemp HCB 83-402

High-temperature lubricant for roller chains in stenter frames

Product data	Klübertemp HCB 83-402
Article number	090083
NLGI grade, DIN 51818	2
Chemical composition	solid lubricant
Chemical composition, type of oil	PFPE
Lower service temperature	-30 °C / -22 °F
Upper service temperature	260 °C / 500 °F
Density at 20 °C	approx. 1.87 g/cm ³
Kinematic viscosity of the base oil, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 100 °C	approx. 40 mm ² /s
Kinematic viscosity of the base oil, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 40 °C	approx. 420 mm ² /s
Corrosion inhibiting properties of lubricating greases, DIN 51802, (SKF-EMCOR), test duration: 1 week, distilled water	<= 1 corrosion degree
Shear viscosity at 25 °C, shear rate 300 s ⁻¹ ; equipment:rotational viscometer	approx. 12 500 mPas
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	60 months

Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 80 years.

Klüber Lubrication München SE & Co. KG / Geisenhausenerstraße 7 / 81379 München / Germany / phone +49 89 7876-0 / fax +49 89 7876-333.

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München SE & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München SE & Co. KG and if source is indicated and voucher copy is forwarded.