

STABURAGS NBU 4 MF, STABURAGS NBU 12 MF

High-performance lubricating greases for the long-term lubrication of rolling and plain bearings



Benefits for your application

- Good pressure resistance in bearings subject to high loads
- Long component life due to good wear protection
- Trouble-free operation due to good sealing and corrosion protection
- Less maintenance due to long-term lubrication
- Emergency lubricating properties for improved functionality in the case of starved lubrication

Description

STABURAGS NBU 4 MF and STABURAGS NBU 12 MF are black lubricating greases based on mineral oil for rolling and plain bearings subject to high loads. The barium complex soap thickener ensures good adhesion of the grease to the lube point and thus good resistance to moisture and aggressive media. Both greases contain special solid lubricants based on MoS₂, which improve emergency lubrication properties under high temperatures or loads.

Both greases are also suitable for steel-on-steel material combinations in slideways and plain bearings.

Application notes

STABURAGS NBU 4 MF / 12 MF are applied by brush, spatula or grease gun. For application via central lubrication systems, pumpability should be checked with the manufacturer beforehand. The friction points can be cleaned with standard detergents.

Application

STABURAGS NBU 4 MF has proven successful for the lubrication of high-speed rolling bearings in rolls, spindles, cam rollers and tensioning rollers. The grease is also used for bearings in compressors and deep drilling machines.

STABURAGS NBU 12 MF is used for highly loaded bearings, e.g. joints, spline shafts, couplings as well as pumps and electric motors, for example in wood drying chambers.

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes	STABURAGS NBU 4 MF	STABURAGS NBU 12 MF
Cartridge 400 g	-	+
Can 1 kg	+	+
Bucket 25 kg	+	+

Product data	STABURAGS NBU 4 MF	STABURAGS NBU 12 MF
Article number	017063	017065
Chemical composition, solid lubricant	molybdenum disulphide	molybdenum disulphide
Chemical composition, thickener	barium complex soap	barium complex soap
Chemical composition, type of oil	mineral oil	mineral oil
Lower service temperature	-20 °C / -4 °F	-15 °C / 5 °F
Upper service temperature	130 °C / 266 °F	130 °C / 266 °F



STABURAGS NBU 4 MF, STABURAGS NBU 12 MF

High-performance lubricating greases for the long-term lubrication of rolling and plain bearings

Product data	STABURAGS NBU 4 MF	STABURAGS NBU 12 MF
Colour space	black	black
Worked penetration, DIN ISO 2137, 25 °C, lower limit value	245 x 0.1 mm	245 x 0.1 mm
Worked penetration, DIN ISO 2137, 25 °C, upper limit value	275 x 0.1 mm	275 x 0.1 mm
Kinematic viscosity of the base oil, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 40 °C	approx. 47 mm ² /s	approx. 220 mm ² /s
Kinematic viscosity of the base oil, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 100 °C	approx. 7 mm ² /s	approx. 19 mm ² /s
Copper corrosion, DIN 51811, (lubricating grease), 24h/100°C	1 - 100 corrosion degree	
Corrosion inhibiting properties of lubricating greases, DIN 51802, (SKF-EMCOR), test duration: 1 week, distilled water	<= 1 corrosion degree	0 corrosion degree
Copper corrosion, DIN 51811, (lubricating grease), 24h/120 °C		1 - 120 corrosion degree
Drop point, DIN ISO 2176, IP 396	>= 220 °C	>= 220 °C
Four-ball tester, welding load, DIN 51350 pt. 04	approx. 4 000 N	>= 4 500 N
Water resistance, DIN 51807 pt. 01, 3 h/90 °C, rating	<= 1 - 90	<= 1 - 90
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	60 months	60 months

Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 80 years.

Klüber Lubrication München SE & Co. KG / Geisenhausenerstraße 7 / 81379 München / Germany / phone +49 89 7876-0 / fax +49 89 7876-333.

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München SE & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München SE & Co. KG and if source is indicated and voucher copy is forwarded.